

**NATROCHEM, INC.**

P.O. BOX 1205
SAVANNAH, GA 31402
(912) 236-4464 FAX: (912) 236-1919
www.natrochem.com

DATA SHEET

Natro-Tar 588

Natro-Tar 588 is 100% pure kiln-burned Wood Tar, imported from Sweden. Natro-Tar 588 is manufactured in a closed vacuum system at high temperatures that do not generate creosote. Also known as Stockholm Tar, it is manufactured and tested under closely controlled conditions to ensure quality and uniformity. Applications include:

Historic Architectural Preservation
Coating of cordage and fish nets
Preservation and fiber
Waterproofing medium for tarpaulins
Coatings and Paints
Insecticides
Authentic shipbuilding
Wound-treatment of trees

This product is not recommended for use in pharmaceuticals, cosmetics, or veterinary medicine.

TEST	TEST METHOD	SPECIFICATION
Acid Number	QCL-8.2.4-2-4	65 Max
Viscosity, SFS @ 122°F	QCL-8.2.4-2-5	500 Max
Specific Gravity, @ 80°F	QCL-8.2.4-2-12	1.01 - 1.06
Moisture, %	QCL-8.2.4-2-7	0.6 Max

TYPICAL PROPERTIES

Acid Number	50
Viscosity, SFS @ 122°F	130
Specific Gravity @ 80°F	1.04
Packaging	pint(1lb.), can(8lb.), Pail(40lb.), Drum(441lb.)
Shipping Point	Savannah Georgia

Date of Revision: 01/13/16 The information in this data sheet is derived from the best available sources and is believed to be accurate. However, no guarantee is expressed or implied regarding the accuracy of these data or the use of this product, nor are any statements in this bulletin intended as recommendations to use our products in the infringement of any patents.

OTHER NATROCHEM PRODUCTS

**DLC® - Rosin Oils - Rosin Pitches - Tarene
Natro-Flex - Tar-Cel- Natro-Cel**