



**NATROCHEM, INC.**  
P.O. BOX 1205  
SAVANNAH, GA 31402  
(912) 236-4464 FAX: (912) 236-1919  
[www.natrochem.com](http://www.natrochem.com)

## **DATA SHEET NATRO-TAC K-85**

Natro-Tac K-85 is a blend of resin and solvent used in adhesives and allied industries. The solids component is a thermoplastic, non-polar hydrocarbon resin polymer with 85°C melt point. The solvent is ethyl acetate. The two components are blended at ambient conditions and drummed at 400 lb net.

<b>TEST</b>	<b>TEST METHOD</b>	<b>SPECIFICATION</b>
Solids Content (%)	QCL-8.2.4-2-12	69-71

### **TYPICAL PROPERTIES**

Solids Content	70.0
Color	clear
Flash Point	-3°C

Original Issue: March 16, 2005

**The information in this data sheet is derived from the best available sources and is believed to be accurate. However, no guarantee is expressed or implied regarding the accuracy of these data or the use of this product, nor are any statements in this bulletin intended as recommendations to use our products in the infringement of any patents.**

### **OTHER NATROCHEM PRODUCTS**

**DLC® - Galex® - Rosin Oils - Rosin Pitches - Tarene™  
Natro-Flex™ - Tar-Cel® - Natro-Cel®**